

## **ORAJET® Series 3751RA Wrapping Cast Digital Media with RapidAir® Technology**

### **Description**

2.25-mil, cast PVC film with a low initial tack adhesive, white gloss surface with RapidAir® technology

### **Release Paper**

101# PE-coated silicone paper featuring an advanced air release technology to facilitate quicker, easier application

### **Adhesive**

Grey, solvent-based, repositionable, permanent low initial tack adhesive can be removed with little or no adhesive residue for up to four years with heat

### **Applications**

Long-term, irregular surfaces such as outdoor signage, and complex vehicle and fleet graphics

### **Technical Data**

<b>Thickness</b> (without protective paper and adhesive)	2.25 mil
<b>Dimensional Stability</b> (FINAT TM-14)	Adhered to steel, no shrinkage in cross direction; In length, <.004"
<b>Temperature Resistance</b>	Adhered to aluminum, -58°F to +212°F, no variation
<b>Fire Behavior</b> (DIN 75200) <b>Fire Rating</b>	Adhered to steel, self-extinguishing ASTM E 84-07 Class "A"
<b>Adhesive Power</b> (FINAT TM-1, after 24 h, average)	Adhered to stainless steel: 4.1 lb/in
<b>Tensile Strength</b> (DIN EN ISO 527) Along Across	Min. 19 MPa Min. 19 MPa
<b>Elongation at Break</b> (DIN EN ISO 527) Along Across	Min. 120% Min. 120%
<b>Seawaterability</b> (DIN 50 021)	Adhered to aluminum, after 100h/73°F, no variation
<b>Shelf Life</b> (68°F/50% relative humidity)	2 years
<b>Minimum Application Temperature</b>	50°F
<b>Available Lengths</b> <b>Available Widths</b> (inches)	150' (50-yard) 30, 54, 60
<b>Minimum Life Expectancy</b> (based on accepted application procedures on vertical surfaces)	8 years (Unprinted)
<b>Recommended Laminates</b>	ORAGUARD® Series 290, 290F, 293

Oracal recommends that printed film is allowed to dry for at least 24 hours at 70°F (48-72 preferred) before applying a laminate.

### **Attention**

Recycling Recommendation: Waste class similar to household waste, is to be recycled according to the local regulations.

Surfaces to which the material will be applied must be cleaned thoroughly of dust, grease or any contaminants. Freshly lacquered or painted surfaces should be allowed to stand for at least three weeks after complete curing. The compatibility of selected lacquers and paints should be tested by the end-user prior to use.

The statements in this information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without any guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications, customers should independently determine the suitability of this material for their specific purpose, prior to use.

**For instant access to more information click on the links below**

### **Profiles**

<http://www.oracal.com/knowledge/icc-profiles.asp>

### **Tech Support**

<http://www.oracal.com/knowledge/contact-support.asp>

### **Find a Distributor**

<http://www.oracal.com/distributors/>

### **General Warranty**

[http://www.oracal.com/\\_userfiles/File/GeneralWarranty.pdf](http://www.oracal.com/_userfiles/File/GeneralWarranty.pdf)



ENGINEERED to PERFORM BETTER.™

Revised 11/11